



- (A) 5'-0" WIDE CONCRETE SIDEWALK
4" THICK, 2500 P.S.I.
6" THICK AT DRIVEWAY
- (B) 6" ABOVE CENTERLINE ROAD GRADE
- (C) SOD or SEED AND MULCH PER F.D.O.T. STANDARD SPECIFICATION SECTION 570. 1' SOD STRIP REQUIRED ADJACENT TO CURB AND AROUND DRAINAGE STRUCTURES.
- (D) 4' WIDE AREA WITH MAX. SLOPE OF 1"/4 FEET
- (E) CONCRETE MIAMI CURB, 2500 P.S.I.
- (F) ASPHALT PAVEMENT:
1-1/2" ASPHALT BITUMINOUS CONCRETE SP-9.5 OR SP-12.5;
MINIMUM MARSHALL FIELD STABILITY 1500.
- (G) BASE:
6" LIMEROCK (LBR 100) COMPACTED TO 98% DENSITY
BASED ON AASHTO T-180 MODIFIED PROCTOR TEST.
OR
6" CRUSHED CONCRETE (LBR 100) COMPACTED TO 98% DENSITY
BASED ON AASHTO T-180 MODIFIED PROCTOR TEST.
- (H) SUB BASE:
6" SUB BASE COMPACTED TO 98% DENSITY BASED ON AASHTO T-180
MODIFIED PROCTOR TEST WITH MINIMUM LBR 40.

NOTE TO ENGINEER:

**ENGINEER TO SELECT
BASE OPTION**

NOTE:

A REPRESENTATIVE OF A CERTIFIED SOIL LABORATORY SHALL BE PRESENT DURING ALL CONSTRUCTION PHASES TO PERFORM ROADWAY COMPACTION AND DENSITY TESTING AS REQUIRED - SEE INDEX R-6(A/B).



STANDARD CONSTRUCTION DETAIL

50' OR 60' R/W/ ROAD SECTION

NTS

INDEX

R-2

MAY 2020